

AMENDMENTS TO THE CLAIMS

Please amend the claims as follows:

Claims 1 to 6 (Canceled)

7. (Previously Presented) A galvanized steel sheet with a particular post-painting corrosion resistance and a particular paint coat image clarity, comprising:

at least one steel sheet portion; and

a galvanized layer provided on a surface of the at least one steel sheet portion, the galvanized layer, consisting essentially of in mass, 1-10% of Mg, 2-19% of Al and 0.001-2% of Si, with a balance of Zn and unavoidable impurities

wherein the galvanized steel sheet has a center line average roughness (Ra) that is at most 1.0 μm and a filtered waviness curve (W_{CA}) that is at most 0.8 μm .

8. (Currently Amended) The galvanized steel sheet according to claim 7, wherein the galvanized layer further consists essentially of at least one element which includes, in mass, at least one of ~~0.01-0.5% of C~~ 0.01-0.5% of Ca, 0.01-0.2% of Be, 0.0001-0.2% of Ti, 0.1-10% of Cu, 0.001-0.2% of Ni, 0.01-0.3% of Co, 0.0001-0.2% of Cr and 0.01-0.5% of Mn.

9. (Previously Presented) The galvanized steel sheet according to claim 7, wherein the galvanized layer includes a metallographic structure which has an $[\text{Mg}_2\text{Si}]$ phase, a $[\text{Zn}_2\text{Mg}]$ phase and a $[\text{Zn}]$ phase that coexist in a substrate of an $[\text{Al}/\text{Zn}/\text{Zn}_2\text{Mg}]$ ternary eutectic structure].

10. (Previously Presented) The galvanized steel sheet according to claim 7, wherein the galvanized layer includes a metallographic structure which has an [Mg₂Si phase], a [Zn₂Mg phase] and an [Al phase] that coexist in a substrate of an [Al/Zn/Zn₂Mg ternary eutectic structure].
11. (Currently Amended) The galvanized steel sheet according to claim 7, wherein the galvanized layer includes a metallographic structure which has an [Mg₂Si phase], a [Zn₂Mg phase], a [Zn phase] and an [Al phase] that coexist in a substrate of an [Al/Zn/Zn₂Mg ternary eutectic structure].
12. (Currently Amended) The galvanized steel sheet according to claim 7, wherein the galvanized layer includes a metallographic structure which has an [Mg₂Si phase], a [Zn phase] and an [Al phase] that coexist in a substrate of an [Al/Zn/Zn₂Mg ternary eutectic structure].